

2. The composition of claim 1 wherein  $n$  is from 250 to 1,000.

3. The composition of claim 1 wherein the ratio of  $(\text{CH}_3)_3\text{SiO}_{0.5}$  units to  $\text{SiO}_2$  units is from 0.525:1 to 0.775:1.

4. The composition of claim 1 where, for each 100 parts of the silanol-terminated diorganopolysiloxane fluid, there are from 5 to 25 parts, by weight, of the resinous copolymer of  $(\text{CH}_3)_3\text{SiO}_{0.5}$  units and  $\text{SiO}_2$  units, and from 15 to 65 parts, by weight, of the reinforcing silica filler.

5. The cured composition of claim 4.

6. A clear, transparent, mold formed by curing the composition of claim 1 with a catalyst selected from the class consisting of lead soaps, tin soaps, and the combination of an organic compound containing an epoxy group and an amine selected from the class consisting of primary amines, secondary amines, and tertiary amines.

## References Cited

## UNITED STATES PATENTS

3,057,469	10/1962	Bond	260—825
3,205,283	9/1965	Modic	260—825
3,036,985	5/1962	Daudt	260—37 X
3,205,197	9/1965	Cohen et al.	260—46.5

## FOREIGN PATENTS

1,311,578	10/1962	France.
-----------	---------	---------

MORRIS LIEBMAN, Primary Examiner

L. T. JACOBS, Assistant Examiner

U.S. Cl. X.R.

15 260—825